

Technical Specification Comparison

PARAMETERS			AROMATIC OILS	
PROPERTIES	UNITS	TEST METHODS	A-711	A-712
Appearance	Attribute	Visual	Opaque Liquid	Opaque Liquid
		ASTMD – 1544		
Viscosity @40°C	CST	ASTMD – 445	–	–
Viscosity @100°C	CST	ASTMD – 445	35 ± 15	30 ± 15
Density @ 30°C	gms/cc	ASTM D – 445	0.98 ± 0.05	0.96 ± 0.05
Flash Point	°C	ASTM D – 92	Min.230	Min.210
Aniline Point	°C	ASTM D – 611	35 ± 15	Max.40
Pour Point	°C	ASTM D – 97	Max.25	Max.25
Volatile Matter at 100 °C	%	ASTM D – 972	Max 1.0	Max 1.5
Carbon Type Analysis	–	ASTM D – 2140	Typical	NA
CA	%		42	–
CN	%		22	–
CP	%		36	–
Compatibility			NR, SBR & PBR	NR,SBR & PBR
Application			Automotive & OTR tyre, Retread Rubber, Moulded & Extruded Product, Conveyor Belts	