

Naphthenic Oil - Witprol N - 520

PARAMETERS			
PROPERTIES	UNITS	TEST METHODS	N - 520
Appearance	Attribute	Visual	Yellow Clear Liquid
ASTMD - 1544	Max 3.0		Max 3.0
Viscosity @40°C	CST	ASTMD - 445	23 ± 5
Viscosity @ 100 ° C	CST	ASTMD - 445	-
Density @ 30 ° C	gms/cc	ASTM D - 445	0.895 ± 0.03
Flash Point	°C	ASTM D - 92	Min 140
Aniline Point	°C	ASTM D - 611	72 ± 5
Pour Point	°C	ASTM D - 97	Max 30
Volatile Matter at 100 ° C / 2hrs.	%	ASTM D - 972	Max 7.0
Carbon Type Analysis	-	ASTM D - 2140	Typical
CA	%	14	18
CN	%		38
CP	%		48
Compatibility			NR, SBR & PBR
Application			Extruded & Moulded Articles, Hawai sheets, LPG Tubes, Shoes soles, Automotive Tubes, etc.