

# Naphthenic Oil - Witprol N - 840

PARAMETERS			
PROPERTIES	UNITS	TEST METHODS	N - 840
Appearance	Attribute	Visual	Clear & Bright
ASTMD - 1544	Max 3.0		
Viscosity @40°C	CST	ASTMD - 445	350 ± 25
Viscosity @ 100 ° C	CST	ASTMD - 445	-
Density @ 30 ° C	gms/cc	ASTM D - 445	0.94 ± 0.03
Flash Point	°C	ASTM D - 92	Min 210
Aniline Point	°C	ASTM D - 611	90 ± 5
Pour Point	°C	ASTM D - 97	Max 0
Volatile Matter at 100 ° C / 2hrs.	%	ASTM D - 972	Max 1.5
Carbon Type Analysis	-	ASTM D - 2140	Typical
CA	%	14	
CN	%		34
CP	%		54
Compatibility			NR, SBR & PBR
Application			Extruded & Moulded Articles, Hawai sheets, LPG Tubes, Shoes soles, Automotive Tubes, etc.