

Paraffinic Oil - Witprol - P - 248 N

PARAMETERS			
PROPERTIES	UNITS	TEST METHODS	P - 248 N
Appearance	Attribute	Visual	Clear Liquid
Colour	Number	ASTMD – 1500	–
ASTMD – 1544	Max 15.0	Max 12.0	Max 0.5
Viscosity @ 40°C	Cst	ASTMD – 455	460 ± 40
Density @ 30°C	gms/cc	ASTM D – 455	0.845 ± 0.05
flash point	°C	ASTM D – 92	Min. 240
Anilibe point	°C	ASTM D – 611	Min. 100
Pour point	°C	ASTM D – 97	Max 1.0
Volatile Matter At 100 °C / 2 hrs	%	ASTM D – 972	Max 0.5
Carbon Type Analysis	–	ASTM D – 2140	Typical
CA	%		12
CN	%	22	33
CP	%		66
Compatibility			EPDM, IIR
Application			Oil Extended EPDM Rubber, Microwave / LCM Cured EPDM Profiles, Heat Resistant Conveyor Belts, Steam Hoses & Butyl Tubes