

Paraffinic Oil - Witprol - P - 248

PARAMETERS			
PROPERTIES	UNITS	TEST METHODS	P - 248
Appearance	Attribute	Visual	Clear Liquid
Colour	Number	ASTMD – 1500	–
ASTMD – 1544	Max 15.0	Max 12.0	Max 1.0
Viscosity @ 40°C	Cst	ASTMD – 455	460 ± 40
Density @ 30°C	gms/cc	ASTM D – 455	0.880 ± 0.05
flash point	°C	ASTM D – 92	Min. 240
Anilibe point	°C	ASTM D – 611	Min. 105
Pour point	°C	ASTM D – 97	Max 1.0
Volatile Matter At 100 °C / 2 hrs	%	ASTM D – 972	Max 0.5
Carbon Type Analysis	–	ASTM D – 2140	Typical
CA	%		8
CN	%	22	22
CP	%		70
Compatibility			EPDM, IIR
Application			Oil Extended EPDM Rubber & Profile, Heat Resistant Conveyor Belts, Steam Hoses & Butyl Tubes