

## Aromatic RPOs Witprol A-711 and A-712 Specification

PARAMETERS			Aromatic RPOs	
PROPERTIES	UNITS	TEST METHODS	A-711	A-712
Appearance	Attribute	Visual	Opaque Liquid	Opaque Liquid
		ASTMD - 1544		
Viscosity @40°C	CST	ASTMD - 445	-	-
Viscosity @100°C	CST	ASTMD - 445	35 ± 15	30 ± 15
Density @ 30°C	gms/cc	ASTM D - 445	0.98 ± 0.05	0.96 ± 0.05
Flash Point	°C	ASTM D - 92	Min.230	Min.210
Aniline Point	°C	ASTM D - 611	35 ± 15	Max.40
Pour Point	°C	ASTM D - 97	Max.25	Max.25
Volatile Matter at 100 °C	%	ASTM D - 972	Max 1.0	Max 1.5
Carbon Type Analysis	-	ASTM D - 2140	Typical	NA
CA	%		42	-
CN	%		22	-
CP	%		36	-
Compatibility			NR, SBR & PBR	NR, SBR & PBR
Application			Automotive & OTR tyre, Retread Rubber, Moulded & Extruded Product, Conveyor Belts, etc.	